

Product Data Sheet

SUMITOMO POLYETHYLENE LLDPE

FS350A

Linear Low Density, Cast Film

Applications	For lamination film, stretch film, and other general purpose film applications. Also for wire and cable applications.
Characteristics	High strength film, non-slip with excellent transparency and processability.
Typical Processing Conditions	Extrusion temperature : 200°C - 280°C

Typical Properties

Physical		Value	Unit	Method
Melt Index	2.16kg	3.1	g/10min	ASTM D1238
Density		0.922	g/cm ³	ASTM D792-A
Thermal		Value	Unit	Method
Melting Temperature		122	°C	DSC
Film		Value	Unit	Method
Tensile Strength at Break	MD / TD	30 / 25	MPa	ASTM D882
Tensile Elongation at Break	MD / TD	680 / 890	%	ASTM D882
Tensile Modulus, 1% Secant	MD / TD	160 / 160	MPa	ASTM D882
Elmendorf Tear Strength	MD / TD	80 / 200	gf	ASTM D1922
Dart Drop Impact		65	g	ASTM D1709
Haze		0.7	%	ASTM D1003
Gloss	45°	150		ASTM D2457
Other		Value	Unit	Method
Flamability		HB		UL94

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications, actual test results may vary

Test pieces preparation condition : as per ASTM D4976

Cast film processing condition : extruder ø55mm, die width 600mm, die gap 1.2mm, temperature 280°C, chill roll temperature 30°C, output 50kg/hr, line speed 75m/min, thickness 20µm

Manufacturer

FS350A is manufactured in Saudi Arabia by Rabigh Refining & Petrochemical Co. (Petro Rabigh). Petro Rabigh is an ISO 9001, ISO 14001, and ISO 45001 certified company.

Regulatory Compliances

Unmodified FS350A complies with the requirements of,

- US FDA Regulation 21 CFR 177.1520 and its amendments
- Regulation (EC) 1935/2004/EC (Framework), EU Commission Regulation 10/2011 (PIM), Commission Regulation (EC) No.2023/2006 (GMP), and their respective amendments

Please contact your nearest SCE representative for more information.

Restriction of Hazardous Substances

The substances regulated under EU Directive 2011/65/EC, and its amendments, on RoHS in electrical and electronic equipment are not used in the manufacturing process, and are therefore not expected to be present in the product.

Storage and Handling

FS350A is supplied in 25kg bags or in bulk containers. It is advisable to store in a well-ventilated storage facility, protected from rain, direct exposure to sunlight, temperature, and dust.

Moisture may accumulate inside the packaging if there is a significant fluctuation in ambient temperature and high relative humidity. If this occurs, customer is strongly advised to dry the resin prior to use. Direct exposure to sunlight and excessive ambient temperature may affect the properties, appearance, and odour characteristic of the resin.

It is recommended to process FS350A within 6 months upon receipt.

Please refer to the Safety Data Sheet (SDS) for information regarding industrial health and safety issues.

Disposal and the Environment

SCE prioritises environmental management in all our operations in responsibility and respect towards the community and the environment.

Unmodified FS350A is readily recyclable, both for reuse via reprocessing and for energy reclamation through incineration. If disposed in landfills, our products, which are inert materials, do not pose pollution risks since they do not generate gaseous or liquid emissions.

SUMITOMO CHEMICAL EUROPE S.A./N.V.

Woluwelaan, 57
B-1830 Machelen, BELGIUM
Phone +32 2 251 0650, Fax +32 2 251 2991
Website sumitomochemical europe.eu

SUMITOMO CHEMICAL EUROPE N.V.

Turkey Liaison Office
Barbaros Mah. Cigdem Sok.No:1, Agaoglu My Office K:10, D:44-45
34746 Bati Atasehir, Istanbul, TURKEY
Phone +90 216 680 3334, Fax +90 216 680 1012

Disclaimer

All information contained in this document is provided in good faith and its sole purpose is to provide information regarding SCE's polymer products. This product catalogue is provided on an "as is" basis. SCE makes no representation, warranty, express or implied and assumes no liability as to the accuracy or completeness of any of the information contained in this product catalogue. The values shown are purely values measured on the product and are not to be considered as guaranteed specifications. Any information on this product catalogue should not be considered as a recommendation. Customer is responsible to ensure that SCE materials, whether used alone or mix with other materials, are suitable for the intended application. SCE expressly disclaims for any and all liability, including direct and indirect loss, consequential loss or damages based on or relating to the use or errors of and omissions of such information in this product catalogue. Information contained herein is NOT intended to announce product availability anywhere in the world. Please contact your nearest SCE representative for more detailed information.